

Carsealer Brush

Revision: 2/02/2024

Page 1 from 1

Technical data

Basis	Synthetic rubber
Consistency	Liquid paste
Density	$\pm 1,19$ g/ml
Viscosity (Brookfield)	Ca. 6.000 mPa.s
Flashpoint	0 °C
Application temperature	5 °C \rightarrow 30 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Carsealer Brush is a sprayable seam sealer based on innovative polymers for the car industry, car body factories and body repair shops.

Properties

- Quickly drying, paintable sealant.
- Can be applied horizontally as well as vertically.
- No filamenting.
- Resists water and mineral oil.
- Permanent elastic filling
- Excellent adhesion
- Can be applied with airless spraying equipment.
- Can be applied in beads as well as wide layers.

Applications

- For the sealing of car body seams, such as metal overlaps, welded and folded seams, in boot and engine space, in doors and for various seam seals.

Packaging

Colour: grey

Packaging: 1 kg tin

Shelf life

2 years in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all metals

Nature: rigid, clean, dry, free of dust and

grease.

Surface preparation: No pretreatment required. We recommend a preliminary adhesion test on any substrate.

Application method

Application method: With spray gun

Cleaning: With White spirit immediately after use (not cured).

Health- and Safety Recommendations

Take the usual labour hygiene into account.

Consult label for more information.

Dangerous. Respect the precautions for use.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.